CNCGLASS
CNC Ucolin Interlayer Technology Co., Ltd.
SHENZHEN, GD, CHINA
Peter Lin · cnc@cncglass.com · WhatsApp / Mobile +86 15013829504
WeChat wecan365 · www.cncglass.com

How to Choose a Solar EVA Encapsulant Manufacturer

The manufacturer is part of the module's bill of materials

In a crystalline module the encapsulant is easy to overlook and expensive to regret. EVA film bonds the glass, cells, and backsheet (or rear glass), keeps moisture and oxygen at bay, and has to stay clear and adherent for the service life the module is sold under. Choosing who makes that film is therefore a production decision, not a stationery purchase. We advise buyers to judge a manufacturer by the stability of the film, the honesty of the data, and the quality of the lamination support that comes with it.



Figure 1. A roll of solar encapsulant film ready for module lamination.

Longevity claims of two decades or more are common in this industry. They are only meaningful if the formulation, the crosslinking window, and the module's own bill of materials have been tested together. A serious manufacturer can discuss peel strength to glass and to the backsheet, shrinkage in both directions, gel content after a defined cycle, optical transmittance in the band the cells actually use, and behavior after damp-heat and ultraviolet exposure. A brochure sentence about "high quality" is not a substitute for those figures.

Metrics that actually move module performance

Visible and near-infrared transmittance decide how much light reaches the cell. A hazy or yellowed film costs power every hour the module operates. Ultraviolet policy is a separate choice: some packages are designed to cut short-wave UV in order to protect the backsheet and the encapsulant itself; others pass a controlled short-wavelength band when the cell can use it. We do not treat "UV transmittance" and "module efficiency" as a single number, and we are wary of claims that a particular cut-off will raise power by a fixed percentage in every climate.

Crosslinking is the other pillar. A practical gel-content target is often in the mid-to-high seventy percent range or above, but the right number is the one that is reached uniformly in your laminator, not the one that looks best on a data sheet. Under-cured film remains thermoplastic and can creep or take up more moisture; over-cured film can be brittle and can hurt adhesion. Peel values, water uptake, volume resistivity, and potential-induced degradation (PID)

behavior then tell you whether the cured film will still be doing its job after heat, humidity, and system voltage have had their say.

What to ask besides the data sheet

Ask how the manufacturer controls thickness and areal density across the roll, how they pack and store the film, and how long a well-stored roll remains inside its process window. EVA is moisture-sensitive in the reel. A supplier who cannot discuss temperature, humidity, and open-time after unpacking is not yet a process partner. Lamination guidance—temperature, vacuum, and hold time for single-chamber and tandem machines—should be offered as a starting window, with the understanding that your line will need a short qualification.

We also look for a manufacturer who will talk about anti-PID formulations, high-transmittance grades, and, where the module design requires it, alternatives such as POE or co-extruded EPE, without pretending that one chemistry is perfect for every cell and every climate. The right question is not “which famous grade name should I buy” but “which formulation and which cycle will keep this module inside its power-warranty assumptions.”

Support after the first trial roll

The value of a manufacturer shows up when a line changes glass, a backsheet, or a cell. Yellowing, bubbles, or a drop in gel content are then process problems to be solved together, not reasons to silently switch vendors every quarter. Stable film, clear documentation, and people who can read a laminator curve will do more for a module maker than a single aggressive price.

That is the basis on which we prefer to work, and it is the basis we recommend when a project team is qualifying a solar EVA encapsulant.

Select a solar EVA manufacturer the way you would select any other reliability-critical material: on measured optical and mechanical properties, on PID and weathering behavior, and on the quality of the process support. The film will be inside the module for its entire working life; the supplier’s habits will be there with it.

Contact Us

Brand: CNCGLASS

Company: CNC Ucolin Interlayer Technology Co., Ltd.
Address: SHENZHEN, GD, CHINA
Contact: Peter Lin
Email: cnc@cncglass.com
WhatsApp / Mobile: +86 15013829504
WeChat: wecan365
Website: www.cncglass.com

We welcome encapsulant qualifications, lamination-window discussions, and comparisons of EVA, POE, and EPE for your module design.